


AF

Traditional Brick & Stone
with AF Group.





Henley Special Reserve



Durability	F2
Crushing Strength	25N/mm ²
Water Absorption	14%
Pack Size	600 no.
MOL Load Size	10,800 no.



Fine Handmade Textured Red Blend



Durability	F2
Crushing Strength	15N/mm ²
Water Absorption	19%
Pack Size	625 no.
MOL Load Size	11,875 no.



Farmhouse Antique



Durability	F2
Crushing Strength	25N/mm ²
Water Absorption	13%
Pack Size	730 no.
MOL Load Size	11,680 no.




Moreton Red Multi



Durability	F2
Crushing Strength	10N/mm ²
Water Absorption	14%
Pack Size	600 no.
MOL Load Size	10,800 no.



Westley Red



Durability	F2
Crushing Strength	10N/mm ²
Water Absorption	14%
Pack Size	552 no.
MOL Load Size	10,488 no.



Grantchester Blend



Durability	F2
Crushing Strength	25N/mm ²
Water Absorption	16%
Pack Size	730 no.
MOL Load Size	11,680 no.



Audley Antique



Durability	F2
Crushing Strength	25N/mm²
Water Absorption	13%
Pack Size	730 no.
MOL Load Size	11,680 no.



Shelford Cream Multi



Durability	F2
Crushing Strength	25N/mm ²
Water Absorption	17%
Pack Size	730 no.
MOL Load Size	11,680 no.



Teversham Mixture



Durability	F2
Crushing Strength	25N/mm ²
Water Absorption	20%
Pack Size	625 no.
MOL Load Size	11,875 no.



St Andrews Multi



Durability	F2
Crushing Strength	12.5N/mm ²
Water Absorption	20%
Pack Size	552 no.
MOL Load Size	11,592 no.



Mystique



Durability	F2
Crushing Strength	17.5N/mm ²
Water Absorption	10%
Pack Size	600 no.
MOL Load Size	10,800 no.



Olde English Red Multi



Durability	F2
Crushing Strength	20N/mm ²
Water Absorption	12%
Pack Size	552 no.
MOL Load Size	10,488 no.



Olde English Buff Multi



Durability	F2
Crushing Strength	12.5N/mm ²
Water Absorption	20%
Pack Size	552 no.
MOL Load Size	11,592 no.